

One side heat sealable at low sealing temperature, other side treated, metallized BOPP film.

Properties

- One side aluminium coated by vacuum metalization with excellent adhesion
- Very broad seal range
- Brilliant metal appearance

Applications

Designed for very high speed horizontal packaging machines.

PROPERTIES	TEST CONDITIONS		UNITS	TYPICAL VALUES				
THICKNESS		μ	18	20	25	30	40
			Gauge	72	80	100	120	160
THICKNESS TOLERANCE		%	5				
UNIT WEIGHT	ASTM D 2673		g / m ²	16.3	18.1	22.7	27.2	36.3
YIELD	ASTM D 2673		m ² / kg	61.3	55.2	44	36.8	27.5
HAZE	ASTM D 1003		%				
GLOSS	ASTM D 2457		%				
OPTICAL DENSITY	MACBETH		2.2				
COEFFICIENT OF FRICTION*	ASTM D 1894	B/B*	< 0.50				
		B/M*		< 0.25				
TENSILE STRENGTH	ASTM D 882	MD	N/mm ²	120 ± 20				
		TD		270 ± 50				
ELONGATION AT BREAK	ASTM D 882	MD	%	190 ± 40				
		TD		45 ± 10				
HEAT SEAL TEMPERATURE	3 Bar / 0.5 Sec		°C	85 - 140				
SEAL STRENGTH	130°C / 3 Bar / 0.5 Sec		N / 15mm	> 2.8				
WVTR	ASTM F 1249 38°C / 90% RH		g / m ² / day	≤ 0.8				
OTR	ASTM D 3985 23°C / 0% RH		cm ³ /m ² /day	≤ 150				
TREATMENT LEVEL	ASTM D 2578		dyne / cm	≥ 36				
HEAT SHRINKAGE	130°C / 7 min	MD	%	≤ 5.0				
		TD		≤ 3.0				

*B/B : Nontreated side to nontreated side

*All COF values are dynamic results

*B/M : Nontreated side to metal

*Since the climatic and storage conditions influence the metallised surface treatment, the dyne level can not be guaranteed.
In-line corona treatment is recommended for lamination. An adequate primer on the metallized surface is suggested for printing.*

The above information is the result of laboratory test which are applied on samples from standart production. Since the varying conditions under which our products used are beyond our control, all of the above results are without guarantee and warranty.

POLİBAK Plastik Film San. ve Tic.A.Ş. AOSB İzmir-TURKIYE

Phone : +90 232 3767970 Fax : +90 232 3767730

Reference No : 2013/09/07

E-Mail : polibak@polibak.com.tr www.polibak.com.tr