

Oppalyte™ 36MO747


Oriented Polypropylene Film

Product Description

White opaque biaxially oriented polypropylene film, coated on one side acrylic, one side PVdC. Provides excellent performances on all packaging machines.

Key Features

- Broad sealing range on acrylic side
- Excellent aroma, oxygen, and moisture barriers
- Superior opacity
- High yield
- Excellent stiffness
- Coatings are mutually compatible and compatible with converter-applies PVdC coatings.
- Excellent base for converty-applied coatings
- Solvent-free coatings
- Ideal support fo water-based ink printing on acrylic side



General

Availability

- ✓ Africa & Middle East
- ✓ Asia Pacific
- ✓ Europe

Features

- ✓ Acrylic Coated
- ✓ Gas Barrier
- ✓ PVdC Coated
- ✓ Flavor & Aroma Barrier
- ✓ Moisture Barrier
- ✓ Sealable PVdC Coated
- ✓ In Lamination Lap Sealable
- ✓ Oxygen Barrier
- ✓ Light Barrier

Applications

- ✓ Biscuits/Cookie/Crackers
- ✓ Confectionery, Sugar
- ✓ Confectionery, Chocolate
- ✓ Household and Detergents
- ✓ Ice Cream
- ✓ Box Overwrap
- ✓ Bakery
- ✓ Frozen Food
- ✓ Crisps and Snacks
- ✓ Confectionery, Gum
- ✓ Fresh Produce
- ✓ Health and Beauty Care
- ✓ Dry Foods and Beverage Powders

Uses

- ✓ Box Overwrap Flexible Packaging
- ✓ VFFS Flexible Packaging
- ✓ HFFS Flexible Packaging
- ✓ Pre-made Bags - Flexible Packaging

Appearance

- ✓ White

Processing Method

- ✓ Cold Seal Adhesive
- ✓ Inner Web Adhesive Lamination
- ✓ Outer Web Adhesive Lamination
- ✓ Solvent Flexographic Printing
- ✓ Solvent Rotogravure Printing
- ✓ Surface Print Unsupported

Revision date

- ✓ October 10, 2013

Properties

Property	Typical Value	Unit	Test Based On
Yield	40.4	m ² /kg	Internal Method
Unit Weight	24.8	g/m ²	Internal Method
Film Thickness	36	μ	Internal Method
Gloss(45°)			
PVdC Surface	100		Internal Method
Light Transmission	22.0	%	Internal Method
Tensile Strength at Break			
200 mm/min pull rate, 120 mm jaw separation			
MD	115	Mpa	Internal Method
TD	170	Mpa	Internal Method
Elongation at Break			
200 mm/min pull rate, 120 mm jaw separation			
MD	130	%	Internal Method
TD	50	%	Internal Method
Dimensional Stability 135°C / 275°F, 7 min			
MD	-5.0	%	Internal Method
TD	-6.0	%	Internal Method
Elastic Modulus			
MD	1500	Mpa	Internal Method
TD	2500	Mpa	Internal Method
Seal Strength (ESM)			
Acrylic/Acrylic			
105°C, 0.034 Mpa, 2 sec	300	g/2.5 cm	Internal Method
PVdC/PVdC			
115°C, 0.034 Mpa, 2 sec	300	g/2.5 cm	Internal Method
Heat Seal Range			
Acrylic/Acrylic	50	°C	Internal Method
PVdC/PVdC	30	°C	Internal Method
Coefficient of Friction			
Acrylic/Acrylic	0.25		Internal Method
PVdC/PVdC	0.35		Internal Method
Water Vapor Transmission Rate			
38°C, 90% RH	4.8	g/m ² /24 hr	Internal Method
23°C, 85% RH	1.1	g/m ² /24 hr	Internal Method
Oxygen Transmission Rate			
23°C, 0% RH	20	cm ³ /m ² /24 hr	Internal Method
Oxygen Transmission Rate (Wet)			
23°C, 75% RH	20.0	cm ³ /m ² /24 hr	Internal Method

Legal Statement

Contact your Jindal Films Customer Service Representative for potential food contact application compliance (e.g. FDA, EU, HPFB). This product is not intended for use in medical applications and should not be used in any such applications.

Processing Statement

- Standard reel winding: Acrylic outside

Footnotes

1. Product may not be available in one or more countries in the identified Availability regions. Please contact your Sales Representative for complete country availability.
2. Tested at 38°C (100°F)/100%RH, then calculated to 90%RH with .90 multiplier.
3. Sample dimensions and conditioning vary due to differences in equipment design.

Typical properties: these are not to be construed as specifications.

© 2013 Jindal Films. Jindal Films, the Jindal Films logo, and other product or service names used herein are trademarks of Jindal Films, unless indicated otherwise. This document may not be distributed, displayed, copied or altered without Jindal Films' prior written authorization. To the extent Jindal Films authorizes distributing, displaying and/or copying of this document, the user may do so only if the document is unaltered and complete, including all of its headers, footers, disclaimers and other information. You may not copy this document to, or reproduce it in whole or in part on, a website. Jindal Films does not guarantee the typical (or other) values. Any data included herein is based upon analysis of representative samples and not the actual product shipped. The information in this document relates only to the named product or materials when not in combination with any other product or materials. We based the information on data believed to be reliable on the date compiled, but we do not represent, warrant, or otherwise guarantee the accuracy, reliability, or completeness of this information; nor do we warrant, expressly or impliedly, the merchantability, fitness for a particular purpose, freedom from patent infringement, or suitability of the products, materials or processes described. The user is solely responsible for all determinations regarding any use of material or product and any process in its territories of interest. We expressly disclaim liability for any loss, damage or injury directly or indirectly suffered or incurred as a result of, or related to, anyone using or relying on any of the information in this document. This document is not an endorsement of any non-Jindal Films' product or process, and we expressly disclaim any contrary implication. The terms "we," "our," "Jindal Films" and "Jindal" are each used for convenience, and may include Films Americas LLC, Jindal Films Americas LLC, Films Europe S.A.R.L. or any companies affiliated with them in the production and sale of film products. There are a number of such affiliated companies, many with names including "Jindal" or "Film". Neither the use of these terms of convenience, nor anything else in this document, is intended to override or supersede the legal separateness of those affiliated companies and responsibility for local action and accountability remains with them.